

Amendments to the Claims:

This listing of claims will replace all prior versions, and listings, of claims in the application:

Listing of Claims:

1. (Original) A method of manufacturing a bismuth based oxide superconducting wire, characterized by the steps of preparing a raw material powder and subjecting the raw material powder to plastic working and heat treatment;
wherein the raw material powder contains superconducting phases comprising Bi, Pb, Sr, Ca, Cu, and O in a composition ration of approximately 2:2:1:2 (Bi+Pb):Sr:Ca:Cu and non-superconducting phases containing Pb;
wherein the composition ratio (Bi+Pb):Sr:Ca:Cu of the raw material powder is approximately 2:2:2:3; and
wherein the ratio of the non-superconducting phases to the superconducting phases is 5 wt% or less.
2. (Original) A method of manufacturing a bismuth based oxide superconducting wire, characterized by the steps of preparing a raw material powder and subjecting the raw material powder to plastic working and heat treatment;
where the raw material powder contains orthorhombic superconducting phases comprising Bi, Pb, Sr, Ca, Cu, and O in a composition ratio of approximately 2:2:1:2 (Bi+Pb):Sr:Ca:Cu; and
wherein the composition ratio (Bi+Pb):Sr:Ca:Cu of the raw material powder is approximately 2:2:2:3.
3. (Original) A method of manufacturing a bismuth based oxide superconducting wire, characterized by the steps of:
preparing a raw material powder;
subjecting the raw material powder to heat treatment of 600°C to 750°C and at oxygen partial pressure of 0.02 atm or less; and
further performing plastic working and heat treatment on the raw material powder after the heat treatment;

wherein the raw material powder contains Bi, Pb, Sr, Ca, Cu, and O in a composition ratio of approximately 2:2:2:3 (Bi+Pb):Sr:Ca:Cu.

4. (Currently Amended) A bismuth based oxide superconducting wire obtained by the manufacturing method according to ~~any one of claims~~ claim 1 ~~to 3~~.

5. (New) A bismuth based oxide superconducting wire obtained by the manufacturing method according to claim 2.

6. (New) A bismuth based oxide superconducting wire obtained by the manufacturing method according to claim 3.